

Firebrick comparison			
	Low	Med	High
Alumina	30	38	50
Density (lb/cu. ft.)	127	135	150
Service Temperature (F)	2372	2462	2642