



### ThermAll B.V. Series Mortars

Item/Brand		WAM-2600	WAM-2800	
Classification Temperature	°C	1430	1760	
Bulk Density	g/cm <sup>3</sup>	1.9	2	
Modulus of Rupture (110 x24h)	Mpa	21	26	
Permanent Linear Change	%	-2.4	-2	
Al <sub>2</sub> O <sub>3</sub>	%	48	56	
SiO <sub>2</sub>	%	48	40.5	
Fe <sub>2</sub> O <sub>3</sub>	%	1	0.8	
CaO+MgO	%	0.3	0.2	
K <sub>2</sub> O+Na <sub>2</sub> O	%	2.6	2.2	
Consumption for Gunning 2mm Thick	kg/m <sup>2</sup>	4.5~6	5~6	
Consumption for Insulating Bricks	kg/1000Pcs	200	200	
Applications		TAI-28	TAI-30	

The above datas are subject to normal manufacturing variations and change without notice.

Results should not be used for specification purpose.